


## Technical data Contraphon™

### Product type

**Contraphon™ 70**

**Contraphon™ 140**



Acoustic and trickling protection nonwoven

### Characteristic properties

Material	100% synthetic fibres, bonded, ari, water and vapour permeable	
Colour	Typ "W" white / Typ "S" black	Typ "W" white / Typ "S" black

### Technical properties

Unit weight	ca. 70 g/m <sup>2</sup>	ca. 140 g/m <sup>2</sup>
Thickness	ca. 0.8 mm	ca. 1.3 mm
Heat conductivity λ W/m K	ca. 0.045	ca. 0.045
Thermal resistance R in m <sup>2</sup> K/W	ca. 0.018	ca. 0.029

### Advantages

- User-friendly (No troublesome stinging, no itching of the skin)
- Fast installation (High tear and tear propagation resistance in all directions)
- Durable (Is not attacked by bacteria or fungi)
- Sound absorbing (Thanks to the open fibre structure)
- Extremely good value for money (Low unit weight)
- Environment-friendly (Free of harmful substances, thermally disposable)

### Important

For increased safety requirements we do recommend Contraphon™ FR.

### Delivery form rolls of

Length	50 m	50 m
Width	100, 200 cm	100, 200 cm
Diameter approx.	22 cm	28 cm

### Function / Application

Perfectly suitable for covering lathing and joints e.g. as protection against trickling through of domestic dust and fine particles from mineral and other absorption materials. Optical enhancement of joints in ceilings and walls.



The values given are average obtained according to internal and external testing. We reserve the right to make changes at any time in accordance with our knowledge, technology and experiences without any notice.